# Carboxylated Graphene Oxide as a Nanocarrier for Drug Delivery of Quercetin as an Effective Anticancer Agent

Fatemeh Yaghoubi<sup>1,2</sup>, Najmeh Sadat Hosseini Motlagh<sup>3</sup>, Ali Moradi<sup>1</sup> and Fateme Haghiralsadat<sup>1,4,5\*</sup>

<sup>1</sup>Department of Clinical Biochemistry, School of Medicine, Shahid Sadoughi University of Medical Sciences, Yazd, Iran; <sup>2</sup>Medical Nanotechnology and Tissue Engineering Research Center, Yazd Reproductive Sciences Institute, Shahid Sadoughi University of Medical Sciences, Yazd, Iran; <sup>3</sup>Dapartment of Biomedical Engineering, Meybod University, Meybod, Iran; <sup>4</sup>Department of Advanced Medical Sciences and Technologies, School of Paramedicine, Shahid Sadoughi University of Medical Sciences, Yazd, Iran; <sup>5</sup>Department of Life Science Engineering, Faculty of New Sciences and Technologies, University of Tehran, Tehran, Iran

#### **OPEN ACCESS**

ABSTRACT

Received: 26 September 2021 Accepted: 29 November 2021 Published online: 13 August 2022

Citation:

Yaghoubi F, Hosseini Motlagh NS, Moradi A, Haghiralsadat F. Carboxylated Graphene Oxide as a Nanocarrier for Drug Delivery of Quercetin as an Effective Anticancer Agent. *Iranian biomedical journal* 2022; 26(4): 324-329. **Background:** Enhancing the therapeutic profile of hydrophobic drugs using the development of biocompatible drug delivery systems is an urgent need. Many types of research have been conducted on graphene derivatives owing to their unique characteristics.

**Methods:** In this survey, QUER, a natural medicine, was loaded on carboxylated GO, and cytotoxicity assay and the uptake of QUER into prostate cancer cells (PC3) were evaluated.

**Results:** The release behavior of QUER was temperature- and pH-sensitive. Although QUER was loaded with high efficiency, the released rate was low (23.25% at pH 5.5 and 42  $^{\circ}$ C). The toxicity and intensity of fluorescence in the FREE QUER were higher than the loaded form.

**Conclusion:** High-capacity loading and controlled release of GO QUER can be recognized as a proper candidate in treating cancer. *DOI: 10.52547/ibj.3598* 

Keywords: Drug delivery systems, Graphene oxide, Nanoparticle, Quercetin

Corresponding Author: Fateme Haghiralsadat

Department of Advanced Medical Sciences and Technologies, School of Paramedicine, Shahid Sadoughi University of Medical Sciences, Yazd, Iran; E-mail: fhaghirosadat@gmail.com

# INTRODUCTION

evelopment of biocompatible drug delivery systems for enhancing the therapeutic profile of hydrophobic drugs is an urgent demand. increase the Nanomaterials can efficacy of hydrophobic agents through enhancing drug solubility and cellular uptake and reducing systemic toxicity. The most important features of a proper drug delivery system are high drug loading capacity and controlled and localized drug release near cancerous cells<sup>[1-3]</sup>. There is a remarkable attention toward the usage of graphene derivatives in biomedical applications owing to their unique properties. However, aggregation of graphene particles in polar solvents has restricted its biomedical applications<sup>[4]</sup>.

Unlike graphene, GO has shown more solubility as

well as more reactive sites for chemical interactions due to the presence of functionalized groups (such as hydroxyl, epoxide, and carboxyl, on its surface<sup>[5,6]</sup>), which can be lead to more application in gene transfection, biosensing, molecular imaging, and drug delivery<sup>[7,8]</sup>. Furthermore, large surface area, varied surface chemistry, and favorable dispersion in polar solution have presented this graphane as an effective drug carrier compared to other carbon nanomaterials<sup>[7,9]</sup>.

The cytotoxicity of GO with and without doxorubicin was assayed on human multiple myeloma cells, presenting the inhibition of cell proliferation by GO/doxorubicin<sup>[10]</sup>. One study has shown greater release of curcumin from PEGylated GO in the basic environment than acidic one<sup>[11]</sup>. Another study used polyvinylpyrrolidone-functionalized GO for the co-

# List of Abbreviations:

**DAPI**, 4',6-diamidino-2-phenylindole; **EE%**, entrapment efficiency; **GO**, graphene oxide; **HFF**, human foreskin fibroblasts; **MTT**, 3–(4, 5-dimethylthiazol-2-yl)-2, 5-diphenyl tetrazolium bromide; **QUER**, quercetin; **UV–Vis**, ultraviolet–visible spectrophotometry

delivery of QUER and gefitinib toward ovarian cancer cells<sup>[12]</sup>.

In the current study, the cytotoxicity effect and cellular uptake rate of FREE QUER and GO QUER in PC3 cell line were investigated.

# MATERIALS AND METHODS

# Materials

QUER (purity >95%), MTT, dimethyl sulfoxide, dialysis bag (MW¼ 12 kDa), and PBS tablets were obtained from Sigma-Aldrich (St. Louis, MO, USA). DIL Stain (1,1'-dioctadecyl-3,3,3',3'-tetramethylindo carbocyanine perchlorate) and DAPI were purchased from Thermo Fisher Scientific (Waltham, MA, USA). GO was produced from GrapheneX (Sydney, Australia).

# Morphological assessment

Scanning electron microscope (Model EM3200, KYKY, China) and Brookhaven Corp Instruments (Holtsville, NY, USA) were used to evaluate the structure and zeta potential of GO. For capturing the images, first,  $5 \mu l$  of suspension was poured on a glass plate to produce a thin layer of film. Then the sample was coated with a gold layer, and the images were recorded by a scanning electron microscope (model EM3200, KYKY, China).

# **Carboxylation of GO**

GO carboxylation was conducted by the following stages: sonicating GO (2 mg/ml) for one hour, adding 72 mg of NaOH and stirring at room temperature for four hours, adding 0.4 ml of HCl (37% v/v), and removing the salts with deionized water by centrifuging at  $4000 \times g$  for 10 min.

# **Drug loading on GO**

GO (1 mg/ml) was mixed with 0.5 mg/ml of QUER (dissolved in ethanol), followed by stirring at room temperature overnight. After removing unbounded drugs via centrifugation (15000  $\times$ g for 10 min), the concentration of QUER was evaluated by a UV–Vis spectrophotometer (Epoch Box 998 America) at 470 nm. Finally, EE% was assessed by the following equation:

EE% = loaded drug on GO (mg ml<sup>-1</sup>)/total drug (mg ml<sup>-1</sup>) × 100

#### Drug release assay

The release amount of QUER from GO was conducted using a 12 kDa cut-off dialysis tube immersing in PBS (pHs 7.4 and 5.5; at 37  $^{\circ}$ C and 42  $^{\circ}$ C), which was stirred for 72 h. Subsequently, 0.5 ml

of dialysis solution was gathered at different time intervals to measure its absorbance via the UV–Vis spectrophotometer. The solution was then substituted with 0.5 ml of fresh PBS. In the end, the percentage of release was assessed based on the total drug-loaded concentration.

#### Cell culture assay

The cell line of human prostate cancer (PC3) was purchased from the Pasteur Institute of Iran (Tehran). Standard conditions for culturing these cells were comprised of DMEM medium, 10% fetal bovine serum, and penicillin–streptomycin, all from Gibco (Grand Island, USA) at 37 °C and 5% CO<sub>2</sub>.

# In vitro evaluation of cellular uptake

Distribution of the FREE QUER and GO QUER in the cells was evaluated using the intensity of fluorescence, which was captured by fluorescence microscopy (Olympus, Japan). Following the culture of the cells in a six-well plate  $(1.5 \times 10^5 \text{ per well})$ , incubation with the FREE and GO QUER was conducted for three hours. Then PBS (pH 7.4) and 95% ethanol solution were used for washing and fixing, respectively. After staining the cells with DAPI (1 mg/ml), images were finally recorded using fluorescence microscopy.

# Cytotoxicity assay

IC<sub>50</sub> values of both FREE and GO QUER were measured by MTT assay. After 48-h incubation of each well with both QUER, the content of wells was removed following the incubation of each well with 90  $\mu$ l of medium and 10  $\mu$ l of MTT (5 mg/ml) for three hours. Dimethyl sulfoxide was used to dissolve the formazan crystals. Ultimately, the absorbance of samples at 570 nm was evaluated by an EPOCH spectrophotometer (Bio-Tek, Winooski, USA).

# Statistical analysis

All data were expressed as the mean  $\pm$  SD, which was analyzed by GraphPad Prism version 6 (GraphPad, San Diego, CA). Also, one-way analysis of variance (ANOVA) and Tukey's multiple comparisons test were used to measure statistical difference, *p* value < 0.05.

#### **RESULTS AND DISCUSSION**

#### **Characterization of compositions**

The sheet layer and broad surface of GO are depicted in Figure 1A<sup>[13,14]</sup>. Determination of zeta potential by dynamic light scattering, as an indicator of surface charge, has a main role in cellular interactions within

[ DOR: 20.1001.1.1028852.2022.26.4.6.3 ]

the physiological system. In fact, attraction or repulsion between the particles was determined by the amount of zeta potential<sup>[15]</sup>. Greater stability has been found in the higher negative or positive value of zeta potential that particles like to disperse. In contrast, the lower value of zeta potential causes the aggregation of particles<sup>[16,17]</sup>. Figure 1B shows the negative zeta potential of GO (-75.0 mV) presenting the existence of COOH group in its surface. Figure 1C indicates the FTIR spectrum of nanomaterials. The OH band vibration in GO-COOH is represented as a wide band at 3301 cm<sup>-1</sup>, while its functional group (C = O) is displayed at 1631 cm<sup>-1[18]</sup>. The hydroxyl and carbonyl groups of QUER have displayed peaks of about 3294 and 1671 cm<sup>-1</sup>, respectively. Also, cyclobenzene peaks appeared at 1614, 1513, and 1457 cm<sup>-1</sup>. The GO QUER represents the GO, functional groups (3301 and

1631 cm<sup>-1</sup>), as well as the QUER-related peaks (3300, 1620 and 1500 cm<sup>-1</sup>), which provide successful loading of QUER on the GO. The UV-Vis spectra of FREE QUER, GO, GO QUER are demonstrated in Figure 1D. The GO spectrum is characterized by a single peak at 230 nm, which is attributed to the molecular transfer of  $\pi \to \pi$  associated with C-C aromatic rings<sup>[19]</sup>. As the maximum FREE QUER absorption is shown at 260 and 370 nm, in the loaded form, in addition to the red shift (260 nm), the 370 nm band is also observed<sup>[11,20]</sup>. Based on the atomic force microscopy images of GO (Fig. 1E), the dimensions of the GO plates are about 0.4 µm, and the thickness of the plates is about 3 nm. As the thickness of each layer of GO is about 0.2-1.1 nm<sup>[21]</sup>, this thickness indicates each GO plate contains 3-10 layers of GO.



**Fig. 1**. (A) GO scanning electron microscope images, (B) GO zeta potential, (C) FTIR spectrum of GO, GO QUER, and QUER, (D) UV–Vis spectrum of GO, GO QUER, QUER, and (E) atomic force microscopy image of GO, indicating less than 10 layers.



Fig. 2. QUER drug release profile from GO QUER.

#### Loading assay

One of the main goals in the drug delivery systems is to obtain the high concentrations of loaded drug. The role of pH for achieving maximum loading of drugs on the GO-COOH is undeniable. For this purpose, the pH of drugs and GO-COOH (5.5-6) is needed to be similar, otherwise the accumulation of GO-COOH leads to low %EE; 84.5% of QUER was successfully loaded on the GO-COOH.

#### Drug release assay

Cancer cells have generally lower pH and higher temperature than normal cells<sup>[22]</sup>. *In vitro*, some important factors, such as pH, buffer temperature around nanoparticles, and GO membrane structure, affect drug release rate. In the present study, pH 7.5 and temperature of 37 °C were considered as a physiological condition, and pH 5.5 and temperature of 42 °C were regarded for cancer cells. The results revealed that the designed GO is sensitive to temperature and pH and results in better delivery of anticancer drugs to tumor cells, which in turn reduces side effects on normal cells. Based on Figure 2, QUER had the highest release rate at pH 5.5 and 23.25% at 42 °C. However, the lowest release rate was related to physiological conditions, 7.69. Our result was comparable to those of studies conducted by Pourjavadi *et al.*<sup>[17]</sup>, Malekmohammadi *et al.*<sup>[23]</sup>, and Omidi *et al.*<sup>[24]</sup>. The low release rate of QUER was linked to its specific structure ans its hydrophobicity, which causes a stronger bond to  $GO^{[24]}$ .

# Cytotoxicity assay

Although the use of chemotherapeutic agents is one of the main approaches to the treatment of cancer, drug resistance and its widespread effects on normal cells have limited effect. The study used a natural anticancer drug, QUER, which is significantly less toxic than commercially potent anticancer drugs, inexpensive, and readily available. MTT assay was performed to evaluate the inhibitory effects of different forms of drugs on PC3 cell line. First, the cytotoxicity of drugfree GO on PC3 cells was investigated. The results showed that GO at a concentration of 1,000 µg/ml had very minor toxicity, while this compound at the dose used in the analysis (200 µg/ml) had no toxicity and no effect on the survival rate of PC3 cells. Following cytotoxicity experiments, the effects of QUER on free and loaded forms were investigated. The results reflected that treatment with free and loaded drugs inhibited the growth of PC3 cells. As illustrated in Figure 3, the free form of the drug is more toxic than the loaded form.

One of the main reasons for the use of nanocarriers in drug delivery is the loading of large amounts of drugs and, at the same time, their slow release to reduce the side effects of chemotherapy drugs. Based on the results, the IC<sub>50</sub> of QUER in the PC3 cell line was  $35.82 \pm 2.84 \mu$ M, while in the loaded form (GO-QUER) increased ( $82.35 \pm 4.55 \mu$ M). Also, The IC<sub>50</sub> of QUER and GO-QUER in the HFF cell line was  $91.10 \pm 7.20$  and  $105 \pm 6.17 \mu$ M, respectively. These result showed that FREE QUER is more toxic than loaded drug, due to the strong binding of QUER to graphene oxide, which reduces its tendency to release. In all



**Fig. 3.** Cytotoxicity analysis of (A) FREE GO for PC3 after 48. Different concentrations of FREE QUER and GO QUER for PC3 (B) and HFF (C) after 48 h.



Fig. 4. Cellular uptake images of PC3 cells, incubated with FREE QUER (A) and GO QUER (B) for 180 min. DAPI (blue) was used for nucleus staining.

treatments, HFF cells, as a normal cell line, have higher  $IC_{50}$  values than cancer cells, indicating less toxicity in normal cells.

loaded on GO relative to the free form presented controlled release and more capability of drug loading, resulting in fewer side effects on normal cells.

# Cellular uptake assay

Cellular uptake of FREE and GO QUER in PC3 cell line is depicted in Figure 4. GO and the nuclei of the cancer cells were stained with DAPI dye and DIL, DiIC18, respectively. These images show the successful delivery of GO and drug-loaded GOs into the cells. QUER emitted red fluorescence. It means that its intensity was higher in the free form of QUER compared to the loaded form because of the quenching property of GO<sup>[25]</sup>. Figure 4 represents lower fluorescence in the HFF cell line compared to PC3 cell line, indicating the lower entry of GO into normal cells. The result of Wu and co-workers<sup>[10]</sup> suggested a similar result of the cellular uptake of free curcumin and curcumin-loaded lipid-polymer hybrid nanoparticles. In the current study, cytotoxicity and cellular uptake of FREE and GO QUER in the PC3 cell line have been studied. While the loading efficiency of QUER on GO was high, the special structure of QUER reduced release rate. Based on the result of release, GO QUER was sensitive to pH and temperature, resulting in the differentiation of normal and cancerous cells. The fewer toxicity of GO QUER rather than FREE OUER displays localized and controlled release, which in turn leads to lesser side effect on normal cells. The effectiveness of GO QUER needs more release of QUER; therefore, photothermal and photodynamic therapy are suggested.

GO was selected as a suitable nanoparticle owing to its bipolar properties and broad surface. While the release rate of QUER was low, its loading efficiency was more than 80%. The release profile was influenced by temperature and pH, which can differentiate normal and cancer cells. The higher  $IC_{50}$  values of the drug

# DECLARATIONS

## Acknowledgments

The authors thank the Biochemistry Department at Shahid Sadoughi University of Medical Sciences and Medical Nanotechnology and Tissue Engineering Research Center, both in Yazd, Iran for their financial support.

# **Ethical statement**

Not applicable.

### Data availability

The analyzed data sets generated during the study are available from the corresponding author on reasonable request.

#### **Author contributions**

FY: prepared the proposal, wrote the manuscript, and performed study analysis; NSHM: wrote the manuscript and performed study analysis; AM wrote the manuscript and performed study analysis; FH conceived the idea and supervised the study. All authors have read and approved the final version of the manuscript.

#### **Conflict of interest**

None declared.

#### **Funding/support**

The present study has financially supported by the Biochemistry Department at Shahid Sadoughi University of Medical Sciences and Medical Nanotechnology and Tissue Engineering Research Center, both in Yazd, Iran.

# REFERENCES

- 1. Islami M, Zarrabi A, Tada S, Kawamoto M, Isoshima T, Ito Y. Controlled quercetin release from high-capacityloading hyperbranched polyglycerol-functionalized graphene oxide. *International journal of nanomedicine* 2018; **13**: 6059.
- 2. Pham TA, Kumar NA, Jeong YT. Covalent functionalization of graphene oxide with polyglycerol and their use as templates for anchoring magnetic nanoparticles. *Synthetic metals* 2010; **160**: 2028-2036.
- Balandin AA, Ghosh S, Bao W, Calizo I, Teweldebrhan D, Miao F, Lau CN. Superior thermal conductivity of single-layer graphene. *Nano letters* 2008; 8(3): 902-907.
- 4. Xu LQ, Yee YK, Neoh KG, Kang ET, Fu GD. Cyclodextrin-functionalized graphene nanosheets, and their host-guest polymer nanohybrids. *Polymer* 2013; **54**: 2264-2271.
- Fang M, Wang K, Lu H, Yang Y, Nutt S. Covalent polymer functionalization of graphene nanosheets and mechanical properties of composites. *Journal of materials chemistry* 2009; 19: 7098-7105.
- 6. Xu Z, Zhu S, Wang M, Li Y, Shi P, Huang X. Delivery of paclitaxel using PEGylated graphene oxide as a nanocarrier. *ACS applied materials and interfaces* 2015; **7**(2): 1355-1363.
- Huang T, Zhang L, Chen H, Gao C. A cross-linking graphene oxide–polyethyleneimine hybrid film containing ciprofloxacin: One-step preparation, controlled drug release and antibacterial performance. *Journal of materials chemistry B* 2015; 3(8): 1605-1611.
- 8. Enayati M, Nemati A, Zarrabi A, Shokrgozar MA. Reduced graphene oxide: An alternative for Magnetic Resonance Imaging contrast agent. *Materials letters* 2018; **233**: 363-366.
- Zhang S, Yang K, Feng L, Liu Z. In vitro and in vivo behaviors of dextran functionalized graphene. *Carbon* 2011; 49(12): 4040-4049.
- Wu S, Zhao X, Cui Z, Zhao C, Wang Y, Du L, Li Y. Cytotoxicity of graphene oxide and graphene oxide loaded with doxorubicin on human multiple myeloma cells. *International journal of nanomedicine* 2014; 9: 1413.
- 11. Charmi J, Nosrati H, Amjad JM, Mohammadkhani R, Danafar H. Polyethylene glycol (PEG) decorated graphene oxide nanosheets for controlled release curcumin delivery. *Heliyon* 2019; **5**(4): e01466.
- 12. Tiwari H, Karki N, Pal M, Basak S, Verma RK, Bal R, Kandpal ND, Bisht G, Sahoo NG. Functionalized graphene oxide as a nanocarrier for dual drug delivery applications: The synergistic effect of quercetin and gefitinib against ovarian cancer cells. *Colloids and surfaces B: biointerfaces* 2019; **178**: 452-459.
- Alibolandi M, Mohammadi M, Taghdisi SM, Ramezani M, Abnous K. Fabrication of aptamer decorated dextran coated nano-graphene oxide for targeted drug delivery. *Carbohydrate polymers* 2017; 155: 218-229.

- 14. Taghavi S, Nia AH, Abnous K, Ramezani M. Polyethylenimine-functionalized carbon nanotubes tagged with AS1411 aptamer for combination gene and drug delivery into human gastric cancer cells. *International journal of pharmaceutics* 2017; **516**(1-2): 301-312.
- Honary S, Zahir F. Effect of zeta potential on the properties of nano-drug delivery systems-a review (Part 2). *Tropical journal of pharmaceutical research* 2013; 12: 265-273.
- 16. Mishra B, Patel BB, Tiwari S. Colloidal nanocarriers: a review on formulation technology, types and applications toward targeted drug delivery. *Nanomedicine: Nanotechnology, biology and medicine* 2010; **6**(1): 9-24.
- 17. Pourjavadi A, Asgari S, Hosseini SH. Graphene oxide functionalized with oxygen-rich polymers as a pH-sensitive carrier for co-delivery of hydrophobic and hydrophilic drugs. *Journal of drug delivery science and technology* 2020; **56**: 101542.
- Motlagh NH, Parvin P, Mirzaie Z, Karimi R, Sanderson J, Atyabi F. Synergistic performance of triggered drug release and photothermal therapy of MCF7 cells based on laser activated PEGylated GO+ DOX. *Biomedical optics express* 2020; 11(7): 3783-3794.
- 19. Lai Q, Zhu S, Luo X, Zou M, Huang S. Ultravioletvisible spectroscopy of graphene oxides. *AIP advances* 2012; **2**(3): 032146.
- da Silva-Buzanello RA, Ferro AC, Bona E, Cardozo-Filho L, de Araújo PHH, Leimann FV, Gonçalves OH. Validation of an ultraviolet–visible (UV–Vis) technique for the quantitative determination of curcumin in poly (l-lactic acid) nanoparticles. *Food chemistry* 2015; **172**: 99-104.
- 21. Schniepp HC, Li JL, McAllister MJ, Sai H, Herrera-Alonso M, Adamson DH, Prud'homme RK, Car R, Saville DA, Aksay IA. Functionalized single graphene sheets derived from splitting graphite oxide. *The journal of physical chemistry B* 2006; **110**(17): 8535-8539.
- 22. Swietach P, Vaughan-Jones RD, Harris AL, Hulikova A. The chemistry, physiology and pathology of pH in cancer. *Philosophical transactions of the royal society B: biological sciences* 2014; **369**(1638): 20130099.
- 23. Malekmohammadi S, Hadadzadeh H, Farrokhpour H, Amirghofran Z. Immobilization of gold nanoparticles on folate-conjugated dendritic mesoporous silica-coated reduced graphene oxide nanosheets: a new nanoplatform for curcumin pH-controlled and targeted delivery. *Soft matter* 2018; **14**(12): 2400-2410.
- 24. Omidi S, Pirhayati M, Kakanejadifard A. Co-delivery of doxorubicin and curcumin by a pH-sensitive, injectable, and in situ hydrogel composed of chitosan, graphene, and cellulose nanowhisker. *Carbohydrate polymers* 2020; **231**: 115745.
- 25. Motlagh NSH, Parvin P, Refahizadeh M, Bavali A. Fluorescence properties of doxorubicin coupled carbon nanocarriers. *Applied optics* 2017; **56**(27): 7498-7503.