

Short Report

Extracellular Production of Silver Nanoparticles by Using Three Common Species of Dermatophytes: *Trichophyton rubrum*, *Trichophyton mentagrophytes* and *Microsporum canis*

Maryam Moazeni¹, Niloofar Rashidi¹, Ahmad R. Shahverdi²,
Fatemeh Noorbakhsh³ and Sassan Rezaie^{*1,4}

¹Div. of Molecular Biology, Dep. of Medical Mycology and Parasitology, School of Public Health, Tehran University of Medical Sciences, Tehran; ²Dep. of Pharmaceutical Biotechnology and Medical Nanotechnology Research Center, School of Pharmacy, Tehran University of Medical Sciences, Tehran; ³Dep. Of Biology, Islamic Azad University, Varamin-Pishva Branch, Varamin; ⁴Dept. of Medical Biotechnology, School of Advanced Medical Technologies, Tehran University of Medical Sciences, Tehran, Iran

Received 13 August 2011; revised 20 December 2011; accepted 21 December 2011

ABSTRACT

Background: To develop a new green approach for biosynthesis of silver nanoparticles, myconanotechnology has been represented as a novel field of study in nanotechnology. In this study, we have reported the extracellular synthesis of highly stable silver nanoparticles using three species of dermatophytes: *Trichophyton rubrum*, *Trichophyton mentagrophytes* and *Microsporum canis*. **Methods:** Clinical strains of these species were grown in a liquid medium containing mineral salt and incubated at 25°C for 5-7 days. The cell-free filtrate of each culture was obtained and subjected to synthesize silver nanoparticles in the presence of 1 mM AgNO₃. **Results:** The reduction of Ag⁺ ions in metal nanoparticles was investigated virtually by tracing the solution color which was switched into reddish-light brown after 72 h. For *T. mentagrophytes*, a UV-visible spectra demonstrating a strong, quite narrow peak located between 422 and 425 nm was obtained. For *M. canis*, a fairly wide peak centering at 441 nm and for *T. rubrum*, a weak spectrum to decipher were observed. According to transmission electron microscopy (TEM) results, fairly uniform, spherical, and small in size with almost less than 50 nm particles were forms in case of *T. mentagrophytes*. For the other two species, TEM images showed existence of small spherical nanosilvers but not as small as nanoparticles synthesized by *T. mentagrophytes*. **Conclusion:** We observed that species belong to a single genus of the fungi have variable ability to synthesize silver nanoparticles extracellularly with different efficiency. Furthermore, the extracellular synthesis may make the process simpler and easier for following processes. *Iran. Biomed. J. 16 (1): 52-58, 2012*

Keywords: Nanoparticles, Dermatophytes, Extracellular biosynthesis

INTRODUCTION

The unique size-dependent characteristics of nanoparticles make them indispensable in many areas of human life ranging from industries like aerospace engineering to natural science, such as medicine, biology and food technology [1]. In aspect of medicine, nanobiotechnology poses an upcoming and rapid developing field with various kinds of applications especially for human therapeutics [2].

Apart from antimicrobial properties, anti-cancer

effect of nanoparticles has been recently documented [1] as well as anti-fungal and anti-tumor drugs using simple delivery systems have already been marketed. Moreover, successful application of nanoparticles in drug delivery and controlled-drug release has been newly reported [3, 4]. Hence, understanding of biological process in nanoscale level is a strong driving force behind development of nanotechnology [5].

In very recent years, the mycosynthesis of metal nanoparticles or myconanotechnology has drawn the attention of researches to the novel field of

*Corresponding author; Tel.: (+98-21) 8895 1392; Fax: (+98-21) 6646 2267; E-mail: srezaie@sina.tums.ac.ir

biosynthesis of nanomaterials. This new field of nanoscience is at the interference of nanotechnology and mycology, comprising an interesting new applied science with considerable potentials owing to the wide range of diversity of fungi [6].

In the world of modern nanoscience which toxic synthesis protocols are being used to obtain the nanoparticles, there is a need to evolve a green approach for nanomaterial synthesis. Therefore, eco-friendly, non-toxic approaches for biosynthesis of nanomaterials and nanostructures have been newly emerged as a promising method to meet the need [7-9]. With respect to this fact, there has been an increasing tendency for re-exploring of microorganisms as potential biofactories for synthesis of functional metallic nanoparticles. The fungal systems or myconanofactories have already been exploited for the biosynthesis of metal nanoparticles of silver, gold, zirconium, silica, titanium, iron (magnetite) and platinum [6] as well as ultrafine oxide nanoparticles, such as Sb_2O_3 [10, 11] and TiO_2 [11].

A large number of fungal strains are capable to synthesize silver nanoparticles (SNP) extracellularly, among which *Fusarium oxysporum* [12], *Bacillus licheniformis* [13], *Aspergillus fumigatus* [14], *Aspergillus niger* [15], *Aspergillus clavatus* [16], *Penicillium brevicompactum* [17], *Cladosporium cladosporioides* [18], *Fusarium semitectum* [19], and yeast strains MKY₃ [20] have been previously described.

As a matter of fact, fungi have some advantages over the bacteria and plants. Fungal mycelia are able to resist the flow pressure, agitation, high temperature and other inappropriate conditions. Furthermore, the extracellular secretion of reductive agents makes the downstream processing easier and finally the mycosynthesized nanoparticles can be directly used in various applications due to the absence of unnecessary cellular components into the experimental solution [21].

Dermatophytes are considered as a real potent skin parasite in public health as to induce superficial skin, hair and nail infections. However, the highly useful utilization of them should not be ignored in nanomycotechnology.

In the present investigation, for the first time, we have reported the extracellular synthesis of highly stable SNP using three more common species of dermatophytes including *Trichophyton rubrum*, *Trichophyton mentagrophytes* and *Microsporum canis*.

MATERIALS AND METHODS

Fungal strains. Three strains of dermatophytes, *T. rubrum*, *T. mentagrophytes* and *M. canis*, were used in

this investigation. The strains were isolated from cutaneous specimens of patients who were referred to Medical Mycology Laboratory, Department of Medical Mycology, Tehran University of Medical Sciences, Iran. The isolates were grown on Sabouraud dextrose agar medium (SDA) and preserved at 25°C until use.

Preparation of cell-free fungal filtrate. The liquid medium containing mineral salts was used to make an efficient medium for fungal growth and establish a biomass competent for SNP biosynthesis. The medium contained (g/l): KH_2PO_4 7.0, K_2HPO_4 2.0, $MgSO_4 \cdot 7H_2O$ 0.1, $(NH_4)_2SO_4$ 1.0, yeast extract 0.6, and glucose 10.0 [16]. The components were mixed completely by stirring on a magnetic stirrer and then the solution was boiled to digest the undissolved substances and filtered through filter paper. Three Erlenmeyer flasks each containing 200 ml of the mentioned medium were inoculated with three testing strains: *T. rubrum*, *T. mentagrophytes* and *M. canis*. The three flasks were incubated aerobically on an orbital shaker at 25°C agitating at 150 rpm. Since the growth rate of dermatophytes is low for getting enough amount of biomass, the flasks were incubated under the mentioned conditions for two weeks. Eventually, 2.5, 0.5 and 1.5 g of biomasses were obtained after this period of time for *T. rubrum*, *T. mentagrophytes* and *M. canis*, respectively. Afterward, the biomasses were extensively washed twice with sterile distilled water and then harvested by sieving through a plastic sieve, followed by extensive washing to remove all medium ingredients. Fresh and clean biomasses were taken into three new flasks containing Milli-Q deionized water with the ratio of 1:10. Then, they were agitated at the same condition as described above but for 72 h. Cell-free filtrates were obtained by utilizing Whatman filter paper No. 1.

Synthesis of silver nanoparticles. Cell-free filtrates were treated with $AgNO_3$ in such a way that a solution with 1 mM of $AgNO_3$ in final concentration was made. The flasks were agitated at 150 rpm in dark. A negative control (only filtrates, without the silver ion) was also run along with the experimental flasks.

Characterization of synthesized SNP. Aliquots of 1ml of the reaction solutions were removed after 72 h and consequently subjected to UV-visible spectroscopy (Labomed Inc., USA). The absorbance was measured at a resolution of 1 nm. The shape and also estimated size of the SNP were determined by transmission electron microscopy (TEM). TEM images of the samples were obtained using a transmission electron microscope (Philips 30ML20, The Netherlands) at a voltage of 100 kv.




Fig.1. Comparison between the color of the solution before and after AgNO_3 addition. **(A)** Cell filtrate at the beginning of the reaction; **(B)** cell filtrates of (a) *T. mentagrophytes*, (b) *M. canis* and (c) *T. rubrum* with silver ion (1 mM) after 72 h of reaction.

Evaluation of Antifungal activity of synthesized SNP. In order to assess the antimicrobial effect of synthesized silver nanoparticles, *Candida albicans* standard strain (ATCC 10261) was applied. The isolate was kept at -80°C as 20% glycerol stocks and were subcultured, as required, on SDA plates at 30°C . Microdilution antifungal susceptibility testing of the *C. albicans* isolate was performed by the broth microdilution method described in CLSI document M27-A3 [22] and performed with SNP and fluconazole as a reference antifungal agent. Silver nanoparticles synthesized by *T. mentagrophytes* were applied as the representative of the nanoparticles produced by three strains. RPMI 1640 medium with L-glutamine and phenol red without bicarbonate and buffered to pH 7.0 with 0.165 mol/L MOPS (3-(N-morpholino) propanesulfonic acid).

Fluconazole was dissolved in sterile diluted water to $64 \mu\text{g/L}$, and then diluted to the final concentration of 0.0125 $16 \mu\text{g/L}$ with the medium according to the standard in the Clinical and Laboratory Standards Institute (CLSI) reference method. After growing on SDA (Merck, Germany) at 35°C for 24 h, the yeasts were re-suspended in culture medium, adjusted with a spectrophotometer at 530 nm wavelength and then diluted in culture medium to prepare a working solution at a concentration of 2.5×10^3 cells/mL and incubated at 35°C for 48 h. All tests were carried out in duplicate. The interpretive criteria for susceptibility to fluconazole were published by the CLSI [22], and were as follows: (i) for fluconazole, susceptible, $\leq 8 \mu\text{g/ml}$; susceptible dose-dependent, 16 to 32 $\mu\text{g/ml}$; and resistant, $\geq 64 \mu\text{g/ml}$. For silver nanoparticles, a solution of $16 \mu\text{g/L}$ was prepared and diluted to the final concentration of 0.0125 - $16 \mu\text{g/L}$ with the

medium. The same inoculum size was applied for SNP susceptibility test. The 96-well plate was incubated at 35°C for 48 h.

RESULTS

Silver reduction. Changing in color of the samples were seen gradually switching from nearly colorless to reddish-light brown after addition of Ag^+ ions into the filtered cell-free cultures in the dark. The intensity of color has been increased during the time of incubation. After 72 h, the process was stopped and the particles were subjected to further analysis. The reduction of the Ag^+ ions into metal nanoparticles was investigated virtually, so that the color of the three solutions changed into reddish-light brown after 72 h of incubation (Fig. 1A). However, control samples (without silver ions) showed no change in color of the cell filtrates when incubated in the same environmental conditions (Fig. 1B). The appearance of a reddish-light brown color in the reaction suggested the formation of SNP [23]. No precipitation was observed within the solutions even after 72 h of incubation.

UV-visible spectroscopy. Determining UV-visible absorption is a rapid, reliable and available tool for ensuring that colloidal silver particles have been formed. The UV spectroscopy method can be applied for size measurement of SNP based on localized surface plasmon resonance band exhibiting at different wavelength. The light absorption pattern of the cell filtrate was monitored after 72 h in the range of 200-800 nm by using UV-visible spectrophotometer (Fig.




Fig. 2. UV-visible spectrum of liquid mediums containing cell filtrates and silver ion (1 mM) for (a) *T. mentagrophytes*, (b) *M. canis* and (c) *T. rubrum*.

2). As illustrated in Figure 2a, a strong quite narrow peak located between 422 and 425 nm was obtained for *T. mentagrophytes*. The average wavelength at which the peak occurred was around 423.5 nm. Observation of this peak which assigns to a surface plasmon is well-

documented for silver metal nanoparticles with sizes much less than 70 nm [24]. Figure 2b indicates a fairly wide peak centering at 441 nm for *M. canis* and Figure 2c shows such a weak spectrum to decipher for *T. rubrum*. However, other tools of determining SNP properties have proved the existence of the particles but with somehow aggression.

Analysis of transmission electron microscopy. TEM analysis was employed to determine the morphology and shape of SNP. The representative TEM image has been indicated in Figure 3. Accordingly for all three testing strains, the majorities of the SNP are relatively uniform in diameter and present in spherical shape. Additionally, TEM images depicted that the particles synthesized by *T. mentagrophytes* are predominantly formed at even less than 50 nm but not for *T. rubrum* and *M. canis*. In other words, the size of particles produced by *M. canis* was more than 50 nm and mostly in the range of 50-70 nm. In case of *T. rubrum*, it was well-demonstrated that the particles were produced in various different sizes, ranging from 50 to more than 100 nm. Moreover, the *T. rubrum* attributed particles were produced in cylindrical rather than spherical shape.

Evaluation of antifungal activity of synthesized SNP. In this study, fluconazole, an antifungal agent which is widely used to treat *Candida*-associated infections, was used as a positive control to compare with SNP. Silver nanoparticles synthesized by *T. mentagrophytes* showed antifungal activity against yeast strain tested and exhibited minimal inhibitory concentration value of 4 $\mu\text{g}/\text{mL}$; however, it was significantly less than fluconazole level. The strain was susceptible dose-dependent against fluconazole, showing minimal inhibitory concentration values of 16 $\mu\text{g}/\text{mL}$ toward the fungal strain tested.




Fig. 3. TEM micrograph of silver particles synthesized by (a) *T. mentagrophytes*, (b) *M. canis* and (c) *T. rubrum* (scale bar: 100 nm).

DISCUSSION

Myconanotechnology represents a novel field of study in nanotechnology and has currently attracted a great deal of attention. In fact, several scientists have re-explored the fungi including yeasts and filamentous fungi as a biofactory for eco-friendly, cost-effective synthesis of nanoparticles particularly SNP [24, 25]. The advantageous of fungal-mediated biosynthesis of nanoparticles have turned the attention of scientists to the kingdom of fungi. The most notable benefits of applying fungi in nanoscience are their resistance to many harsh conditions as well as secretion of extracellular reductive proteins so that it makes the downstream processes easier [20].

The unusual physicochemical and optoelectronic properties of nanoparticles present them as beneficial candidates for utilization in various fields of natural science including drug and gene delivery [26, 27], biodetection of pathogens [28], probing of DNA structure [29], tumor destruction [30] and tissue engineering [31]. Although living microorganisms are built up cells that are typically 10 μ M across, the cell parts are much smaller than this so that the typical size of proteins is just 5 nm which is comparable with the dimensions of artificial nanoparticles [1]. Accordingly, the idea of using nanoparticles as small probes is being arisen. Consequently, it allows researchers to get the inspiration from cellular mechanisms without too much interference [32]. Therefore, innovation of new approaches for cost-effective, non-toxic and eco-friendly synthesis of nanoparticles is preferred nowadays.

The formation of nanoparticles has been reported by many investigators so far, both intracellular and extracellular. For example Ahmad *et al.* [23] reported the ability of the fungus *Fusarium oxysporum* for the synthesis of silver nanoparticles. Sastry *et al.* [26] demonstrated the intracellular synthesis of silver nanoparticles of 2-25 nm within *Verticillium*. Moreover, in 2006, Bhainsa and d'Souza [14] and in 2008, Gade *et al.* [15] reported the ability of soil-born *Aspergillus* to produce extracellular silver nanoparticles. In 2009, Balaji *et al.* [18] used *Cladosporium cladosporioides* for the extracellular synthesis of spherical silver nanoparticles from an aqueous solution of a silver salt. In comparison with other fungi, investigated dermatophytes were able to form bigger nanoparticles except *T. mentagrophytes*.

In the present study, three species of dermatophytes were applied to assess their ability of producing SNP and at last, we achieved notable results which enable us to compare extracellularly the various capacities of different species of dermatophytes in producing SNP.

It was observed that upon addition of the silver ion (1 mM) into the flask containing the cell filtrate, the color

of the medium turned into light yellowish-brown (Fig. 1). The intensity of color increased due to excitation of surface plasmon vibrations in the metal nanoparticles. This significant observation indicates that the reduction of the Ag⁺ ions takes place extracellularly.

The unique optical properties of metal nanoparticles originate from the collective oscillations of conduction electrons are termed surface plasmon polariton resonances (SPPR) [24]. It is well known that the shape of SPPR spectrum and the wavelength at which the maximum absorbance is occurred is strongly related to the particle size and relative dimensions [33]. Therefore, increasing in particle size makes the SPPR peak move to longer wavelength [33]. Also, the size of SNP has a linear correlation with the peak intensity.

The UV-visible spectrum in Figure 2 shows the SPPR peak of SNP at 422 and 423.5 nm for *T. mentagrophytes* and *M. canis*, respectively. As the spectrums depict, the particles are likely to be less than 70 nm in size and are fairly monodispersed in case of particles synthesized by *T. mentagrophytes*. Unfortunately, no certain peak was observed for *T. rubrum*. Nevertheless, switching of the solution color to yellow as well as evidences of TEM analysis demonstrated that the SNP exist.

In fact, all three strains have successfully synthesized SNP, but *T. mentagrophytes* produced much more desirable particles in aspect of shape and dimensions.

The studies of Duran *et al.* [34] raise the possibility that formation of SNP by *Fusarium oxysporum* is mediated by two distinct mechanisms: One is through nitrate reductase and the other by shuttle quinone process. Similarly, it is also reported that NADH-dependent nitrate reductase is the main enzyme responsible for the reduction of silver ions [35].

Therefore, owing to the fact that the extracellular proteins secreted by the fungi are in charge of the reduction of Ag⁺ to Ag⁰, it is suggestive to investigate the role of reductase in the fungal filtrate to figure out why some species of dermatophytes produce SNP more efficiently than the other species.

The significant feature of silver is its broad spectrum antimicrobial property. Accordingly, several researchers have studied the antimicrobial activity of SNP against bacterial and fungal strains like *E. coli*, *Staphylococcus aureus* (methicillin-resistant *staphylococcus aureus*), *P. aeruginosa*, *Candida albicans* and HIV virus. Moreover, antimicrobial activity of wound dressings covering with SNP has been successfully examined against several common pathogens [36-39].

Our results for evaluation the antimicrobial properties of synthesized silver nanoparticles were consistent with other researches so that the antifungal properties of the synthesized SNP were accurately proven. In addition to notable anti-*Candida* characteristics, it was well demonstrated that the

inhibitory effect of synthesized SNP was even more effective than the antifungal drug, fluconazole.

In conclusion, extracellular synthesis of SNP is highly beneficial because no extra process is required to separate the particles from the living cells. Dermatophytes have potential for extracellular biosynthesis of SNP. In this investigation, it was observed that species of the same genus of the fungi have the ability to synthesize SNP with different efficiency.

ACKNOWLEDGEMENTS

The authors thank the Central Research Laboratory of School of Public Health for providing laboratory facility. We also thank Dr. Saeed Sepehrisresht for helping us with the TEM imaging. This research has been financially supported by a Tehran University of Medical sciences (TUMS) grant. The authors declare that there is no conflict of interests.

REFERENCES

- Salata O. Applications of nanoparticles in biology and medicine. *J Nanobiotechnology*.2004 Apr;2(1):3.
- Saravanan M, Nanda A. Extracellular synthesis of silver bionanoparticles from *Aspergillus clavatus* and its antimicrobial activity against MRSA and MRSE. *Colloids Surf B Biointerfaces*.2010 Jun;77(2):214-8.
- Gelperina S, Kisich K, Iseman M, Heifets L. The potential advantages of nanoparticle drug delivery systems in chemotherapy of tuberculosis. *Am J Respir Critic Care Med*.2005 Dec;172(12):1487-90.
- Pandey R, Khuller GK. Nanoparticle-based oral drug delivery system for an injectable antibiotic-streptomycin. Evaluation in a murine tuberculosis model. *Chemotherapy*.2007;53(6):437-41.
- Whitesides GM. The 'right' size in nanobiotechnology. *Nat Biotechnol*.2003 Sep;21(10):1161-5.
- Gade A, Ingle A, Whiteley C, Rai, M. Mycogenic metal nanoparticles: progress and applications. *Biotechnol Lett*.2010 May;32(5):593-600.
- Sadowski Z, Maliszewska I, Grochowalska B, Polowczyk I, Kozlecki T. Synthesis of silver nanoparticles using microorganisms. *Mater Sci-Poland*.2008;26(2):419-24.
- Jha, A., Prasad, K. and Kulkarni, A. Biosynthesis of selenium nanoparticles. *Int. J. Nanopart.* (in press)
- Jha AK, Prasad K. A green low-cost biosynthesis of Sb2O3 nanoparticles. 2009; *Biochem Eng J*.43(3):303-6.
- Jha AK, Prasad K, Kulkarni AR. Synthesis of TiO2 nanoparticles using microorganisms. *Colloids Surfaces B Biointerfaces*.2009 Jul;71(2):226-9.
- Anil Kumar S, Abyaneh MK, Gosavi SW, Kulkarni SK, Pasricha R, Ahmad A et al. Nitrate reductase-mediated synthesis of silver nanoparticles from AgNO₃. *Biotechnol Lett*.2007 Mar;29(3):439-45.
- Kalimuthu K, Suresh Babu R, Venkataraman D, Bilal M. and Gurunathan S. Biosynthesis of silver nanocrystals by *Bacillus licheniformis*. *Colloids Surf B Biointerfaces*.2008 Aug;65(1):150-3.
- Bhainsa KC, D'Souza SF. Extracellular biosynthesis of silver nanoparticles using the fungus *Aspergillus fumigatus*. *Colloids Surf B Biointerfaces*.2006 Feb;47(2):160-4.
- Gade AK, Bonde P, Ingle AP, Marcato PD, Durán N, Rai MK. Exploitation of *Aspergillus niger* for synthesis of silver nanoparticles. *J Biobased Mater Bioenergy*. 2008 Sep;2(3):243-7.
- Verma VC, Kharwar RN, Gange AC. Biosynthesis of antimicrobial silver nanoparticles by the endophytic fungus *Aspergillus clavatus*. *Nanomedicine (Lond)*. 2010 Jan;5(1):33-40.
- Shaligram NS, Bule M, Bhambure R, Singhal RS, Singh SK, Szakacs G et al. Biosynthesis of silver nanoparticles using aqueous extract from the compactin producing fungal strain. *Proc Biochem*.2009;44(8):939-43.
- Balaji DS, Basavaraja S, Deshpande R, Mahesh DB, Prabhakar BK, Venkataraman A. Extracellular biosynthesis of functionalized silver nanoparticles by strains of *Cladosporium cladosporioides* fungus. *Colloids Surf B Biointerfaces*.2009 Jan;68(1):88-92.
- Basavaraja S, Balaji SD, Lagashetty A, Rajasab AH, Venkataraman A. Extracellular biosynthesis of silver nanoparticles using the fungus *Fusarium semitectum*. *Mat Res Bul*.2008 May;43(5):1164-70.
- Kowshik M, Ashtaputre S, Kharrazi S, Vogel W, Urban J, Kulkarni SK et al. Extracellular synthesis of silver nanoparticles by a silver-tolerant yeast strain MKY3. *Nanotechnology*.2003;14(1):95-100.
- Narayanan KB, Sakthivel N. Biological synthesis of metal nanoparticles by microbes. *Adv Colloid Interface Sci*. 2010 Apr;156(1-2):1-13.
- Instituts, C.a.L.S. Reference method for broth dilution antifungal susceptibility testing of yeasts. CLSI document M27-A3. Clinical and Laboratory Standards Instituts: Wayne, Pennsylvania, USA.
- Ahmad A, Mukherjee P, Senapati S, Mandal D, Khan M, Kumar R et al. Extracellular biosynthesis of silver nanoparticles using the fungus *Fusarium oxysporum*. *Colloids and Surfaces B: Biointerfaces*.2003;28(4):313-8.
- Evanoff DD Jr, Chumanov G. Synthesis and optical properties of silver nanoparticles and arrays. *ChemPhysChem*.2005;6(7):1221-31.
- Mandal D, Bolander ME, Mukhopadhyay D, Sarkar G, Mukherjee P. The use of microorganisms for the formation of metal nanoparticles and their application. *Appl Microbiol Biotechnol*.2006 Jan;69(5):485-92.
- Sastry M, Ahmad A, Islam KM, Kumar R. Biosynthesis of metal nanoparticles using fungi and actinomycete. *Curr Sci*.2003;85(2):162-70.
- Mah C, Zolotukhin I, Fraites T, Dobson J, Batich C, Byrne BJ. Microsphere-mediated delivery of recombinant AAV vectors *in vitro* and *in vivo*. *Mol Ther*.2000;1:S239-S42.
- Pantartotto D, Partidos C, Hoebeke J, Brown F, Kramer, E, Briand J et al. Immunization with peptide-

- functionalized carbon nanotubes enhances virus-specific neutralizing antibody responses. *Chem Biol.*2003 Oct; 10(10):961-6.
28. Edelstein RL, Tamanaha CR, Sheehan PE, Miller MM, Baselt DR, Whitman LJ et al. The BARC biosensor applied to the detection of biological warfare agents. *Biosensors and Bioelectronics.*2000 Jan;14(10-11):805-13.
 29. Mahtab R, Rogers JP, Murphy CJ. Protein-sized quantum dot luminescence can distinguish between "straight", "bent", and "kinked" oligonucleotides. *J Am Chem Soc.*1995 Sep;117(35):9099-100.
 30. Shinkai M, Yanase M, Suzuki M. Intracellular hyperthermia for cancer using magnetite cationic liposomes. *J Magn Magn Mater.*1999 Apr;194(1-3):176-184.
 31. Ma J, Wong H, Kong LB, Peng KW. Biomimetic processing of nanocrystallite bioactive apatite coating on titanium. *Nanotechnology.*2003;14(6):619.
 32. Taton T. Nanostructures as tailored biological probes. *Trends Biotechnol.*2002 Jul 20(7):277-9.
 33. Schmoll HJ, Kollmannsberger C, Metzner B, Hartmann JT, Schleucher N, Schoffski P et al. Long-term results of first-line sequential high-dose etoposide, ifosfamide, and cisplatin chemotherapy plus autologous stem cell support for patients with advanced metastatic germ cell cancer: an extended phase I/II study of the German Testicular Cancer Study Group. *J Clin Oncol.*2003 Nov; 21(22):4083-91.
 34. Jaidev LR, Narasimha G, Fungal mediated biosynthesis of silver nanoparticles, characterization and antimicrobial activity. *Colloids Surf B Biointerfaces.*2010 Dec;81(2):430-3.
 35. Duran N, Marcato PD, Alves OL, Souza GI, Esposito, E. Mechanistic aspects of biosynthesis of silver nanoparticles by several *Fusarium oxysporum* strains. *J Nanobiotechnology.*2005 Jul;3:8.
 36. Anil Kumar S, Abyaneh MK, Gosavi SW, Kulkarni SK, Pasricha R, Ahmad A, Khan MI. Nitrate reductase-mediated synthesis of silver nanoparticles from AgNO₃. *Biotechnol Lett.*2007Mar;29(3):439-45.
 37. Rai M, Yadav A, Gade A Silver nanoparticles as a new generation of antimicrobials. *Biotechnol Adv.*2009 Jan-Feb;27(1):76-83.
 38. Kim KJ, Sung WS, Suh BK, Moon SK, Choi JS, Kim JG et al. Antifungal activity and mode of action of silver nano-particles on *Candida albicans*. *Biometals.*2009Apr; 22(2): 235-42.
 39. Elechiguerra JL, Burt J., Morones JR, Camacho-Bragado A, Gao X, Lara HH et al. Interaction of silver nanoparticles with HIV-1. *J Nanobiotechnology.*2005; 3:6.